

Gråpap, syrefri, glat

Material composition: 100 % grey waste paper

Grammage scope: 960 - 2520 g/m²

Main applications: production of office supplies (ring binders, folders,), painting templates, covers, mirror frames, board games, boxes, upholstered furniture

Basic information:

- Durable and resistant to bending
- Both sides smooth grey
- Environmentally friendly, made from 100% recyclable materials
- Shade: Grey / natural
- pH value 7

STANDARD TECHNICAL SPECIFICATION

Parameter	Unit	Tolerance	Value				
			960	1265	1890	2210	2520
Grammage	g/m ²	+/- 5%	960	1265	1890	2210	2520
Thickness	mm	+/- 5%	1.5	2.0	3.0	3.5	4.0
Humidity	%	+/- 2%	6.5	6.5	6.5	6.5	6.5
Bulk	cm ³	Mini	1.56	1.58	1.58	1.58	1.59
Taber stiffness - longitudinal	MD	+/- 1%	3700	6200	-	-	-
Taber stiffness - transversal	CD	+/- 10%	1100	2300	-	-	-

Storage conditions:

Paper should be stored in a dry place in its original packaging. Prior to use in production, air conditioning of an open paper pallet is required for a minimum of 24 hours in the conditions of the production hall.

Note: The aforementioned parameters are reference values and can be subject to change without prior notice.

TECHNICAL SHEET

