



KRS ApS
Mandals Allé 9A
DK-5500 Middelfart

Order no. 524098-1
Page 1 of 1
Appendices 1
Initials elm/troj/hbs

Gregersensvej
DK-2630 Taastrup
Tel. +45 72 20 20 00
Fax +45 72 20 20 19
info@teknologisk.dk
www.teknologisk.dk

Test Report

- Material:** Boracol 20.
According to assignor the product contents 17,25 % DOT. This was confirmed by chemical analysis performed by Laboratory for Chemistry and Microbiology. Reg no. 37553-1.
- Method:** EN 46-1, 2009: *Wood preservatives - Determination of the preventive action against recently hatched larvae of Hylotrupes bajulus (Linnaeus) - Part 1: Application by surface treatment (laboratory method.)*

EN 73, 1988: *Wood preservatives – Accelerated ageing of treated wood prior to biological testing. – Evaporative ageing procedure.*
- Result:** Accredited the test was performed by MPA, Eberswalde, see enclosed report no. 32/13/9684/01. (3 pages)
- Assessment:** The product is found effective against recently hatched larvae of *Hylotrupes bajulus* at an application rate on 500mL /m².

Note: The interpretation of this test report and the practical conclusions that can be drawn from it require a basic knowledge of the problems of wood preservation. For this reason this test report alone does not indicate any official approval of the wood preservative tested.

18-02-2014, Danish Technological Institute, Wood Technology

Elisabeth Morsing
Ph. Direct: +45 72 20 23 35
E-mail: elisabeth.morsing@teknologisk.dk

Test responsible

Trine Østergaard Jensen
Ph. Direct: +45 72 20 13 90
E-mail: troj@teknologisk.dk

Co-signatory