

TEST REPORT: 7191038612-CHM12-CSY

Date: 2 AUG 2012

Tel: +65 68851335 Fax: +65 67784301

Client's Ref: 205Q1207044

Email: sihai.li@tuv-sud-psb.sg

Note: This report is issued subject to the Testing and Certification Regulations of the TÜV SÜD Group and the General Terms and Conditions of Business of TÜV SÜD PSB Pte Ltd. In addition, this report is governed by the terms set out within this report.



PSB Singapore

Choose certainty.
Add value.

SUBJECT

Evaluation of "Reflecto" comply with Singapore Green Labelling Scheme (SGLS), Category 032.

CLIENT

PT Citra Megah Selecomindo
Ruko Gading Bukit Indah Blok B No.8
Jln. Bukit Gading Raya – Kelapa Gading
Jakarta 14240
Indonesia


Attn : Mr. Rahmat Rahardja Ong

DESCRIPTION OF SAMPLE

One bottle of sample labelled as "Reflecto" was received on 08 Jun 2012.

DATE OF TEST

16 July 2012 – 3 Aug 2012



Laboratory:
TÜV SÜD PSB Pte. Ltd.
No.1 Science Park Drive
Singapore 118221

Phone : +65-6885 1333
Fax : +65-6776 8670
E-mail: testing@tuv-sud-psb.sg
www.tuv-sud-psb.sg
Co. Reg : 199002667R

Regional Head Office:
TÜV SÜD Asia Pacific Pte. Ltd.
3 Science Park Drive, #04-01/05
The Franklin, Singapore 118223
TÜV[®]

TEST REPORT: 7191038612-CHM12-CSY

2 AUG 2012



PSB Singapore

METHOD OF TEST

The sample was tested in the "as-received" condition.

<u>Test</u>	<u>Method</u>
1) Formaldehyde	The sample was analysed by UV-Vis Spectrophotometer using Acetylacetone as reagent.
2) Mercury, Lead, Cadmium and Chromium	The sample was digested in inorganic acid, followed by analysis using Inductively Coupled Plasma Atomic Emission Spectroscopy (ICP-AES).
3) Flash point @ 61°C	By Seta Flash.
4) Volatile organic compound content	By BS EN ISO 11890-2:2006, Paints and varnishes – <i>Determination of volatile organic compound (VOC) content – Part 2 : Gas-chromatographic method.</i>
5) Halogenated solvents Aromatic solvents Epichlorohydrin	By Gas Chromatograph –Mass Spectrometry (GC-MS).
6) N-methyl pyrrolidone	By Gas Chromatography with Flame Ionization Detector (GC-FID)
7) Alkyl Phenol Ethoxylates	BS3762 : 1990 Analysis of formulated Detergent

SUMMARY OF TEST RESULTS

The summary of test results for "Reflecto".

Item No.	Test	Result	Method Detection Limit	GLS032 Criteria	Inferred Remark
1	Formaldehyde Content	Not Detected	0.1%	Not Detected	Pass
2	Heavy Metals: Mercury, Lead, Cadmium, Chromium	Not Detected	0.01%	Not Detected	Pass
3	Flash point @ 61°C	No Flash	-	> 61°C	Pass
4	VOC Content	21.4 g/L	2 g/L	< 50 g/L*	Pass
5	Halogenated solvents	Not Detected	0.1%	Not Detected	Pass
6	Epichlorohydrin	Not Detected	0.1%	Not Detected	Pass
7	Aromatic solvents	Not Detected	0.1%	Not Detected	Pass
8	N-methyl pyrrolidone	Not Detected	0.1%	Not Detected	Pass
9	Alkyl Phenol Ethoxylates	Not Detected	0.01%	Not Detected	Pass

* For Water Based Coatings (Matt or Low Sheen)

TEST REPORT: 7191038612-CHM12-CSY
2 AUG 2012



PSB Singapore

RESULTS

Table 1 : The Formaldehyde results for "Reflecto".

Test	Result	Method Detection Limit
Formaldehyde Content	Not Detected	0.1%

Table 2 : The Elemental results for "Reflecto".

Test	Result	Method Detection Limit
Mercury	Not Detected	0.01%
Lead	Not Detected	0.01%
Cadmium	Not Detected	0.01%
Chromium	Not Detected	0.01%

Table 3 : The Flash Point results for "Reflecto".

Test	Result
Flash point @ 61°C	No Flash

Table 4 : The Volatile Organic Compound (VOC) content for "Reflecto".

Test	Result	Method Detection Limit
VOC Content ^a	21.4 g/L ^b	2 g/L

a) Volatile organic compound (VOC) means any organic compound having an initial boiling point less than or equal to 250°C measured at a standard pressure of 101,3kPa.

b) The result was calculated based on the specific gravity = 1.28Kg/L provided by the client

Table 5 : The analytical results for "Reflecto".

Test	Result	Method Detection Limit
Halogenated solvents	Not Detected	0.1%
Epichlorohydrin	Not Detected	0.1%
Aromatic solvents	Not Detected	0.1%
N-methyl pyrrolidone	Not Detected	0.1%
Alkyl Phenol Ethoxylates	Not Detected	0.01%

MS CHOO SEOW YAH
TECHNICAL EXECUTIVE

for **DR LISIHAI**
AVP / SENIOR CHEMIST
MICROCONTAMINATION DIAGNOSIS
CHEMICAL & MATERIALS

TEST REPORT: 7191038612-CHM12-CSY

2 AUG 2012



PSB Singapore

Please note that this Report is issued under the following terms :

1. This report applies to the sample of the specific product/equipment given at the time of its testing/calibration. The results are not used to indicate or imply that they are applicable to other similar items. In addition, such results must not be used to indicate or imply that TÜV SÜD PSB approves, recommends or endorses the manufacturer, supplier or user of such product/equipment, or that TÜV SÜD PSB in any way "guarantees" the later performance of the product/equipment. Unless otherwise stated in this report, no tests were conducted to determine long term effects of using the specific product/equipment.
2. The sample/s mentioned in this report is/are submitted/supplied/manufactured by the Client. TÜV SÜD PSB therefore assumes no responsibility for the accuracy of information on the brand name, model number, origin of manufacture, consignment or any information supplied.
3. Nothing in this report shall be interpreted to mean that TÜV SÜD PSB has verified or ascertained any endorsement or marks from any other testing authority or bodies that may be found on that sample.
4. This report shall not be reproduced wholly or in parts and no reference shall be made by the Client to TÜV SÜD PSB or to the report or results furnished by TÜV SÜD PSB in any advertisements or sales promotion.
5. Unless otherwise stated, the tests were carried out in TÜV SÜD PSB Pte Ltd, No.1 Science Park Drive Singapore 118221.

July 2011

