


## URKIRAPID J-13

Q/D Synthetic Enamel J-13 Matt Black



### DESCRIPTION



Quick-drying enamel for interior and exterior use. It stands out for its high coverage, good body, quick drying and matte appearance.

It is ideal for painting bodywork parts, smithy work and machinery in general.

### COLORS



URKIRAPID

J-13 MATT BLACK

### SURFACE PREPARATION









On steel: The surfaces to be painted must be properly derusted and degreased.

For a better adhesion and protection of the support, it can be previously primed with F-29 or F-809.

On old paint, sand and degrease previously.

## APPLICATION



 Application viscosity Dilution %	20-25" URKISOL 300 20-25%
 Gravity Gun Application pressure	1.3-1.5 mm 3-4 bar
 Number of coats Total thickness	2 coats 30-40 µm
 Flash time	5-10'
 Drying Time 20°C	30'
 % Gloss 60°-60°	<5

Can be repainted after 24 hours.

---

**SAFETY INSTRUCTIONS**

The use of appropriate personal protective equipment is recommended during application, to prevent the irritation of the respiratory tract, skin and eyes. For professional use only.

---

**STORAGE**

Keep in a tightly covered container, in a dry and ventilated place, avoiding direct exposure to sunlight. Temperature above 5°C is recommended, between 15 and 30°C optimal.

---

**VOC**

The VOC content of URKIRAPID J-13 is a maximum of 550 g/l.

---

The information contained in this Technical Specification Sheet is based on the knowledge and experience of the BESA technical department, and with it it's intended to advice and inform, being the responsibility of the user to take the necessary measures to guarantee the intended purpose of the product. **FOR PROFESSIONAL USE ONLY.**

---