SPRAY URKI**ZINC**

Cold Plating

DESCRIPTION

Primer of acrylic nature for the retouching and repair of damages in galvanised parts, welding joints, structural steel etc. that must be matched in their colour shade. It is used in sectors such as automotive, metal components, DIY, fences, metal doors, etc.

It gives surfaces an appearance similar to hot zinc plating.

COLORS

SPRAY URKI**ZINC**	METALLIC SILVER

SURFACE PREPARATION

Metal supports must be derusted, degreased and dry. If corrosion is present, it must be removed with a wire brush or by sanding.

It can also be applied to pre-sanded aluminium.

USE

Shake the can for about 2-3 minutes before using the Cold Galvanised Zinc-Alu Spray.

Apply 2-3 thin coats leaving 5 - 10 min. between coats.

After use, invert the can and clean the cap.

APPLICATION

Shake can	2-3’
Painting distance	20-30 cm
Number of coats Total thickness	2-3 10-20 µm
Flash time	5-10’
Drying Time	15’

It can be recoated within the first 12 hours after drying.

SAFETY INSTRUCTIONS

The use of appropriate personal protective equipment is recommended during application, to prevent the irritation of the respiratory tract, skin and eyes. For professional use only.

STORAGE

Keep in a tightly covered container, in a dry and ventilated place, avoiding direct exposure to sunlight. Temperature above 5°C is recommended, between 15 and 30°C optimal.

CAUTION: Under no circumstances should the packaging exceed 50°C.

VOC

The VOC content of URK**IZINC** Spray is a maximum of 840 g/l in compliance with European regulation 2004/42/EC IIB(E) (840) <840 g/l.

The information contained in this Technical Specification Sheet is based on the knowledge and experience of the BESA technical department, and with it it's intended to advice and inform, being the responsibility of the user to take the necessary measures to guarantee the intended purpose of the product. **FOR PROFESSIONAL USE ONLY.**