



ACS-55

Thin-wall heat shrink tubing / flexible / flame retardant / 2:1

Features:

- Crosslinked Polyolefin • Shrink ratio: 2:1 • Flame retardant
- General purpose • High flexibility

Approvals:

- UL224 125 °C VW-1 600 V file E526134 • CSA C22.2 No. 198.1-06
- Meets: RoHS, Sony-SS-00259

Application:

- Operating temperature: -55 °C to +125 °C
- Minimum shrink temperature: +70 °C
- Minimum full recovery temperature: +100 °C
- Longitudinal change: 0 ± 10% max.

Order information:

- Colors: black, red, blue, yellow, green, white, purple, brown, orange, grey
- Other colors are available on request



For electronic, automotive and consumer goods.

Flexible, flame retardant, low shrinking temperature.

Free from harmful substances such as PBB's, PBBO's, PBBE's.

Type / Size	As supplied: inside diameter in mm (min.)	After recovery: inside diameter in mm (max.)	After recovery: wall thickness in mm (+/- 0,05)	Reel / Meter
ACS-55 1,2/0,6	1,2	0,6	0,33	150
ACS-55 1,6/0,8	1,6	0,8	0,36	150
ACS-55 2,4/1,2	2,4	1,2	0,44	150
ACS-55 3,2/1,6	3,2	1,6	0,44	150
ACS-55 4,8/2,4	4,8	2,4	0,51	75
ACS-55 6,4/3,2	6,4	3,2	0,56	75
ACS-55 9,5/4,8	9,5	4,8	0,56	75
ACS-55 12,7/6,4	12,7	6,4	0,65	50
ACS-55 16,0/8,0	16,0	8,0	0,69	50
ACS-55 19,0/9,5	19,0	9,5	0,80	30
ACS-55 25,4/12,7	25,4	12,7	0,90	30
ACS-55 32,0/16,0	32,0	16,0	0,90	30
ACS-55 38,1/19,0	38,1	19,0	1,00	30
ACS-55 50,8/25,4	50,8	25,4	1,00	30
ACS-55 76,2/38,1	76,2	38,1	1,20	15
ACS-55 102,0/50,8	102,0	50,8	1,30	15
ACS-55 126,0/63,5	126,0	63,5	1,30	15
ACS-55 150,0/76,0	150,0	76,0	1,30	15

We certify that the values provided are as accurate as possible. Use of these values, however, remains the sole responsibility of the customer and cannot in any way substitute for testing the product under real conditions of use. The user must assess whether this product is suitable for a particular use. KACAB shall not be held responsible for any loss or anomaly resulting from the correct or incorrect use of this product.