

DUAL WALL TUBING

ADW-300/400

Flexible flame retardant, high shrink ratio























ADW-300/400

Dual-wall heat shrink tubing / flexible / flame retardant / 3:1 / 4:1 / adhesive lined

Features:

- Crosslinked co-extruded adhesive lined Polyolefin Shrink ratio: 3:1 and 4:1
- Flame retardant Excellent sealing and insulation properties UV resistant

Approvals

- UL 224 125°C VW-1 600 V file E526134 CSA C22.2 No. 198.1-06 (except clear)
- Meets: SAE-AMS-DTL-23053/4 Meets: RoHS

Application:

- Operating temperature: -55 °C to +125 °C Minimum shrink temperature: +70 °C
- Minimum full recovery temperature: +110 °C Longitudinal change: 0 ± 10% max.

Order information:

- · Color: black
- · Other colors: red, blue, yellow, green, white, clear
- · Also available in various lengths and in mini boxes



For electronic, automotive and consumer goods.
Waterproofing, electrical insulation/

protection.

Free from harmful substances such as PBB's, PBBO's, PBBE's.

Type / Size	As supplied: inside diameter in mm (min.)	After recovery: inside diameter in mm (max.)	After recovery: wall thickness in mm (min.)	Standard length
ADW-300 3/1	3,0	1,0	1,00	1,22 m / 150 m
ADW-300 4,8/1,5	4,8	1,5	1,00	1,22 m / 75 m
ADW-300 6/2	6,0	2,0	1,00	1,22 m / 75 m
ADW-300 9/3	9,0	3,0	1,40	1,22 m / 50 m
ADW-300 12/4	12,0	4,0	1,60	1,22 m /30 m
ADW-300 19/6	19,0	6,0	2,15	1,22 m / 30 m
ADW-300 24/8	24,0	8,0	2,40	1,22 m / 30 m
ADW-300 30/10	30,0	10,0	2,40	1,22 m / 30 m
ADW-300 40/13	40,0	13,0	2,40	1,22 m / 30 m
ADW-400 4/1	4,0	1,0	1,00	1,22 m / 150 m
ADW-400 6/1,5	6,0	1,5	1,00	1,22 m / 75 m
ADW-400 8/2	8,0	2,0	1,00	1,22 m / 75 m
ADW-400 12/3	12,0	3,0	1,40	1,22 m / 50 m
ADW-400 16/4	16,0	4,0	1,60	1,22 m / 30 m
ADW-400 24/6	24,0	6,0	2,15	1,22 m / 30 m
ADW-400 32/8	32,0	8,0	2,40	1,22 m / 30 m
ADW-400 52/13	52,0	13,0	2,40	1,22 m

For cross references, please see pages 4-5

We certify that the values provided are as accurate as possible. Use of these values, however, remains the sole responsibility of the customer and cannot in any way substitute for testing the product under real conditions of use. The user must assess wether this product is suitable for a particular use. KACAB shall not be held responsible for any loss or anomaly resulting from the correct or incorrect use of this product.