TECNOTHANE® automotive parts: Driving advances in





TECNOTHANE® automotive parts

Offering a very low compression set alongside very good elongation properties, our TECNOTHANE® engineering elastomers for the automotive industry are most commonly used to form spring aids for suspension and vibration dampening systems - helping to protect vehicles, and any luggage or cargo, from damage.







Technical properties

TYPICAL PHYSICAL PROPERTIES	UNIT	TEST METHOD	Tecnocell	Evocell MX2
Tensile strength	MPa	ASTM D3574E	6	5
Elongation at break	%	ASTM D3574E	500	450
Tear resistance (trouser specimen)	kN/m	ASTM D3574F	20	10
Compression set at 70°C / 23h	%	ASTM D3574D	8	7,5
Density	g/cm³	ASTM D3574A	0,60	0,50
Minimum service temperature	°C	INTERNAL	-20	-30
Available density range	g/cm ³	ASTM D3574A	0,30 - 1,00	0,30 - 0,60



Enriching lives through innovation

Europe

Tecnoelastomeri S.r.I.Polyurethane Systems

and Machines
Via Magellano, 7/9/11
41013 Castelfranco Emilia
(MO) Italy

Telephone +39 059 92 07 07

Contact:

Nicolaas Weyns Sales Manager nicolaas_weyns@huntsman.com

USA

Huntsman Polyurethanes 2190 Executive Hills Boulevard Auburn Hills, MI 48326 Telephone +1 248 322 7300

Contact:

Nicholas McNeal
Sales Excellence Manager
nicholas mcneal@huntsman.com

China

Huntsman Chemistry R&D Center (Shanghai) Co. No 479 Wen Jing Road Minhang Development Zone Shanghai 200245 Telephone +86 21 3357 2883

Contact:

Lesley Chi Business Head APAC lesley_chi@huntsman.com

www.tecnoelastomeri.com www.huntsman.com

About Huntsman:

Huntsman Corporation is a publicly traded global manufacturer and marketer of differentiated and specialty chemicals with 2016 revenues of more than \$7 billion. Our chemical products number in the thousands and are sold worldwide to manufacturers serving a broad and diverse range of consumer and industrial end markets. We operate more than 75 manufacturing, R&D and operations facilities in over 30 countries and employ approximately 10,000 associates within our four distinct business divisions. For more information about Huntsman, please visit the company's website at www.huntsman.com.

Huntsman Corporation warrants only that its products meet the specifications stated in the sales contract. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications. While all the information presented in this document is believed to be reliable and to represent the best available data on these products, HUNTSMAN MAKES NO WARRANTY OR GUARANTEE OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHT OF ANY THIRD PARTY, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND ANY USER OF PRODUCTS DESCRIBED HEREIN SHOULD CONDUCT A SUFFICIENT INVESTIGATION TO ESTABLISH THE SUITABILITY OF ANY PRODUCT FOR ITS INTENDED USE AND ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES. Products may be toxic and require special precautions in handling. For all products described herein, the user should obtain detailed information on toxicity, together with proper shipping, handling, and storage procedures, and should comply with all applicable safety and environmental standards. The behavior, hazards and/or toxicity of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which may not be known to Huntsman. It is the sole responsibility of the user of such products to evaluate the manufacturing circumstances and the final products under actual end-use requirements and to adequately advise and warn future purchasers and users thereof.

TECNOTHANE® is a registered trademark of Huntsman Corporation or an affiliate thereof in one or more, but not all, countries.

Copyright © 2019 Huntsman Corporation or an affiliate thereof. All rights reserved.